



HEAT INSULATING CARDBOARD

Presentation

Description : Heat insulating cardboard without asbestos
Use : Thermal insulation, tightness
 (Glassworks, steel industry, ovens, etc....)
Size : 500 x 500 mm

Color	White
Limit temperature	1.100 °C
Density	1.10
Coefficient of thermal conductivity	0.12 W/m.°K
Loss of ignition at 800 °C	15 %
Longitudinale	50 kg/cm ²
Transversale	40 kg/cm ²
Shrinkage at 1,000 °C (24 hours)	1 %
Compressibility according to ASTM F 36 k method (70kg/cm ²)	7 %
Elastic recovery	50 %

Tariffs

Thickness (mm)	4 plate batch (€ Excl. tax) 500 mm x 500 mm
3	36,71
5	68,40
10	135,70



CARRIAGE COSTS ARE CALCULATED ACCORDING TO
THE DELIVERY POINT

